

SACADA Database Code: 602

Topology: 4³T178-CA

of independent nodes (IN): 3
Transitivity: [3797]
Space Group: P4/mmm
Pearson: tP24
Coordination Number (CN): 4

Year: 2021

Data

Name	Pressure, GPa	Density, g/cm ³	Gap, eV	Relative energy, eV/atom	Bulk, GPa	Shear, GPa	Vickers, GPa	Refs
4 ³ T178-CA (SACADA #602)		2.494		1.207	213.6	108.1	13.9	SACADA ¹
4 ³ T178-CA								doi: 10.1038/s41524-021-00491-y 

Elasticity tensor (kBar)¹

2812.1110	1047.8052	1720.9240	0.0000	0.0000	0.0000
1047.8052	2812.1110	1720.9240	-0.0000	0.0000	0.0000
1720.9240	1720.9240	6547.0890	-0.0000	-0.0000	0.0000
0.0000	-0.0000	-0.0000	1684.4762	-0.0000	0.0000
-0.0000	0.0000	-0.0000	-0.0000	783.7543	-0.0000
0.0000	0.0000	0.0000	-0.0000	-0.0000	783.7544

¹ We apply the density functional theory (DFT) approach by using the Vienna Ab Initio Simulation Package (VASP) to calculate the total energy and properties of carbon allotropes.

DFT calculations

We apply the density functional theory (DFT) approach by using the Vienna Ab Initio Simulation Package (VASP) package [6] to calculate the total energy of carbon allotropes. The Generalized Gradient Approximation [7] (GGA) for exchange-correlational functional is used everywhere. The energy cutoff set to 600 eV. Fully automatic Γ -centered k-points mesh with a reciprocal-space resolution of $2\pi \times 0.025 \text{ \AA}^{-1}$ is applied. We used tetrahedron method with Blöchl corrections to perform the k-point integration. The convergence thresholds are set at 10^{-6} eV for energy and 10^{-5} eV $\text{\AA}^{-1}$ for ionic forces. Polycrystalline elastic moduli — the bulk modulus, the shear modulus, Young’s modulus, and the Poisson’s ratio ν — have been calculated within the Voigt-Reuss-Hill [8] approximation. The Vicker’s hardness H_v has been estimated according to Oganov’s model [9].