SACADA Database Code: 624

Topology: sqc8102

# of independent nodes (IN): 2
Transitivity: [2564]
Space Group: I4/mmm
Pearson: tI32
Coordination Number (CN): 4

Year: 2021

Data

Name	Pressure, GPa	Density, g/cm³	Gap, eV	Relative energy, eV/atom	Bulk, GPa	Shear, GPa	Vickers, GPa	Refs
sqc8102 (SACADA #624)		2.370		1.469	161.9	113.4	13.3	SACADA[1]
sqc8102								doi: 10.1038/s41524-021-00491-y

Elasticity tensor (kBar)[1]

1862.3432	651.2879	1378.0185	-0.0000	0.0000	0.0000
651.2879	1862.3432	1378.0185	-0.0000	-0.0000	0.0000
1378.0185	1378.0185	7304.6981	-0.0000	-0.0000	0.0000
-0.0000	-0.0000	-0.0000	1218.1556	0.0000	0.0000
0.0000	0.0000	0.0000	-0.0000	1241.3698	0.0000
0.0000	0.0000	0.0000	0.0000	0.0000	1241.3699

[1] We apply the density functional theory (DFT) approach by using the Vienna Ab Initio Simulation Package (VASP) to calculate the total energy and properties of carbon allotropes.

DFT calculations

We apply the density functional theory (DFT) approach by using the Vienna Ab Initio Simulation Package (VASP) package [6] to calculate the total energy of carbon allotropes. The Generalized Gradient Approximation [7] (GGA) for exchange-correlational functional is used everywhere. The energy cutoff set to 600 eV. Fully automatic Γ-centered k-points mesh with a reciprocal-space resolution of $2\pi \times 0.025$ Å^{-1} is applied. We used tetrahedron method with Blöchl corrections to perform the k-point integration. The convergence thresholds are set at 10^{-6} eV for energy and 10^{-5} eV Å^{-1} for ionic forces. Polycrystalline elastic moduli — the bulk modulus, the shear modulus, Young's modulus, and the Poisson's ratio ν — have been calculated within the Voigt–Reuss–Hill [8] approximation. The Vicker's hardness H_v has been estimated according to Oganov's model [9].