## **SACADA Database Code: 671**

Topology: 4<sup>4</sup>T39-CA

# of independent nodes (IN): 4

Transitivity: [4982] Space Group: I2/m Pearson: mS24

Coordination Number (CN): 4

Year: 2023

## **Data**

Name	Pressure, GPa	Density, g/cm³	Gap, eV	Relative energy, eV/atom	Bulk, GPa	Shear, GPa	Vickers, GPa	Refs
4 <sup>4</sup> T39-CA (SACADA #671)		3.451		0.342	416.7	466.1	87.3	SACADA <sup>1</sup>
4 <sup>4</sup> T39-CA								doi: 10.1107/S205252062300255X ជ

## Elasticity tensor (kBar)1

10849.1081	1000.7894	1145.2888	-0.0000	-0.0000	-111.3023
1000.7894	10729.7641	517.9587	-0.0000	-0.0000	437.6914
1145.2888	517.9587	10614.7434	-0.0000	-0.0000	8.5882
-0.0000	-0.0000	-0.0000	5165.7138	313.3247	-0.0000
-0.0000	-0.0000	-0.0000	313.3247	3814.1275	-0.0000
-111.3023	437.6914	8.5882	-0.0000	-0.0000	4620.9823

<sup>&</sup>lt;sup>1</sup> We apply the density functional theory (DFT) approach by using the Vienna Ab Initio Simulation Package (VASP) to calculate the total energy and properties of carbon allotropes.

## **DFT calculations**

We apply the density functional theory (DFT) approach by using the Vienna Ab Initio Simulation Package (VASP) package [6] to calculate the total energy of carbon allotropes. The Generalized Gradient Approximation [7] (GGA) for exchange-correlational functional is used everywhere. The energy cutoff set to 600 eV. Fully automatic  $\Gamma$ -centered k-points mesh with a reciprocal-space resolution of  $2\pi \times 0.025~\text{Å}^{-1}$  is applied. We used tetrahedron method with Blöchl corrections to perform the k-point integration. The convergence thresholds are set at  $10^{-6}$  eV for energy and  $10^{-5}$  eV Å<sup>-1</sup> for ionic forces. Polycrystalline elastic moduli — the bulk modulus, the shear modulus, Young's modulus, and the Poisson's ratio  $\nu$  — have been calculated within the Voigt-Reuss-Hill [8] approximation. The Vicker's hardness  $H_{\nu}$  has been estimated according to Oganov's model [9].