

## SACADA Database Code: 22

Topology: [bto](#) <sup>↗</sup>

# of independent nodes (IN): 1

Transitivity: [1221]

Space Group: P6222

Pearson: hP6

Coordination Number (CN): 3

Year: 1990

## Data

Name	Pressure, GPa	Density, g/cm <sup>3</sup>	Gap, eV	Relative energy, eV/atom	Bulk, GPa	Shear, GPa	Vickers, GPa	Refs
bto (SACADA #22)		3.149		1.379	382.3	209.8	25.7	SACADA <sup>1</sup>
H-6		3.4	Metal		580			doi: <a href="#">10.1557/JMR.1990.2273</a> <sup>↗</sup>
H-6		3.17			372			doi: <a href="#">10.1103/PhysRevB.43.6742</a> <sup>↗</sup>
6(3)6-09		3.19						doi: <a href="#">10.1016/S0009-2614(01)00126-9</a> <sup>↗</sup>
H-6		3.16			370			doi: <a href="#">10.1007/978-94-010-1013-9_1</a> <sup>↗</sup>
H-6					384			doi: <a href="#">10.1103/PhysRevB.78.125415</a> <sup>↗</sup>
H-6								<a href="#">link</a> <sup>↗</sup>
H-6		3.093	Metal					doi: <a href="#">10.1039/c2cp43221h</a> <sup>↗</sup>
H-6								doi: <a href="#">10.1038/srep04339</a> <sup>↗</sup>
H-6			Metal		273			doi: <a href="#">10.1016/j.commatsci.2013.10.032</a> <sup>↗</sup>
H-6								doi: <a href="#">10.1039/c6ra10809a</a> <sup>↗</sup>

## Elasticity tensor (kBar)<sup>1</sup>

6016.8621	3359.7431	922.7967	0.0000	0.0000	0.0000
3359.7431	6016.8621	922.7967	0.0000	-0.0000	-0.0000
922.7967	922.7967	12494.5814	-0.0000	0.0000	-0.0000
0.0000	0.0000	-0.0000	1328.5595	0.0000	0.0000
0.0000	-0.0000	0.0000	0.0000	1992.7088	-0.0000
0.0000	-0.0000	-0.0000	0.0000	-0.0000	1992.7070

<sup>1</sup> We apply the density functional theory (DFT) approach by using the Vienna Ab Initio Simulation Package (VASP) to calculate the total energy and properties of carbon allotropes.

## DFT calculations

We apply the density functional theory (DFT) approach by using the Vienna Ab Initio Simulation Package (VASP) package [6] to calculate the total energy of carbon allotropes. The Generalized Gradient Approximation [7] (GGA) for exchange-correlational functional is used everywhere. The energy cutoff set to 600 eV. Fully automatic  $\Gamma$ -centered k-points mesh with a reciprocal-space resolution of  $2\pi \times 0.025 \text{ \AA}^{-1}$  is applied. We used tetrahedron method with Blöchl corrections to perform the k-point integration. The convergence thresholds are set at  $10^{-6}$  eV for energy and  $10^{-5}$  eV  $\text{\AA}^{-1}$  for ionic forces. Polycrystalline elastic moduli — the bulk modulus, the shear modulus, Young's modulus, and the Poisson's ratio  $\nu$  — have been calculated within the Voigt-Reuss-Hill [8] approximation. The Vicker's hardness  $H_v$  has been estimated according to Oganov's model [9].